

DMI30 SSR SEALANT NON-SKINNING



Product Overview: DMI30 is a non-hardening, self-healing sealant that provides superb adhesion in all conditions; including extreme temperatures and moisture levels. DMI30 does not string during application, and exhibits outstanding webbing and cut-off characteristics. DMI30 is intended for concealed application away from sunlight. This material remains permanently tacky and flexible after curing, and provides a long-lasting and resilient seal.

Product Uses: DMI30 adheres to a wide variety of substrates, and as such serves as a trusted sealant in a multitude of markets. In the metal building industry, DMI30 is often used as a standing seam sealer. It adheres to painted metals, Zincalume, Galvalume, and Kynar 500. DMI30 is also used as a joint sealant in foam glass applications.

Technical Information:

Raw Material BaseCross-Linked Rubber	OdorOdorless
Viscosity2 – 3 Million Centipoise	Water PenetrationNone
ColorTan/Gray	Service Temp. Range-60° – 200°F
Specific Gravity1.4 – 1.5	Application Temp. Range5° – 120°F
Solids91.2%	VOC Content87 g/L
Corrosive PropertiesNone	Manufactured StateTubes, Pails, Drums
Low Temp. FlexibilityNo Adverse Effects	Shelf Life12 Months

Application Information: Ensure substrates are clean, dry, and free of oil and moisture. Exercise care during application to prevent air or contaminant entrapment. This product can be applied by standard hand or air-powered caulking guns. For bulk applications, use a Graco 55:1 ratio pump with fluid pressure of 40 to 50 psi. Once applied, do not handle, move, or pack for one hour. Panels bonded by this product can easily be separated for repair and maintenance, even after extended periods of time.

Safety Instructions: CAUTION! This product contains mineral spirits. Keep away from sparks, heat, and open flame. Overexposure can cause nausea. Consult the product SDS for detailed safety information.

Contact Us: For more information regarding this product and others, please contact us at:

DMI Direct Metals, Inc.	PH 239-599-8527
1719 Baseline Court	E: orders@directmetalsinc.com
Fort Myers, FL 33905	